


# Concorde Anthracite Mate 60x60 Rc 20mm Antislip



## Technical Data



Series: CONCORDE  
 Product: Concorde Anthracite Mate 60x60 Rc 20mm Antislip  
 Size: 60x60  
 Sales group G.5182  
 Type: Porcelain tiles

Type of material Coloured body  
 Slipresness R: R11C  
 Class: Antislip  
 UPEC:  
 Finish: MATT

Size	Product type	Pcs/Box	M2/Box	Kg/Box	Boxes/Pallet	M2/Pallet	Kg/Pallet
	Field Tile	2	0,720	33,834	30,000	21,600	1015,020

Please note: the contents of this packaging list are for guidance only, the contents of the packaging may vary. Please consult our sales staff for the exact list.

Variations




## **Variations**

**Technical Data**

**Concorde Anthracite Mate 60x60 Rc 20mm Antislip**

Family: **Porcelain tiles MATT**  
 Absortion Group: **Bla**  
 Size:  
 Worz Size (mm): **600 x 600 x 20**



**PHYSICAL CHARACTERISTICS**

CHARACTERISTICS	STANDARD	VALUE
Dimensional tolerances and surface appearance	UNE-EN-ISO 10545-2	Complies with the standar
Water Absortion	UNE-EN-ISO 10545-3	E<0,5%
Breaking strenght (N)	UNE-EN-ISO 10545-4	>1300
Flexural tensile strengthn (N/mm2)	UNE-EN-ISO 10545-4	>=35
Resistance to abrasion (PEI)	UNE-EN-ISO 10545-7	2
Thermal shock resistance	UNE-EN-ISO 10545-9	Complies with the standar
Cracking resistance	UNE-EN-ISO 10545-11	Complies with the standar
Frost resistance	UNE-EN-ISO 10545-12	Complies with the standar
Scratch hardness according to Mohs	UNE-EN-ISO 67101	8
Slipperness resistance   Pendulum	UNE-EN 16165:2022 anexo C	Clase 3
Slipperness resistance   Inclined platform	UNE-EN 16165:2022 anexo B	R11
Slipperness resistance   Barefoot areas	UNE-EN 16165:2022 anexo A	C
Reaction to fire	UNE-EN-ISO 13501-1	A1 - A1 FL
DCOF	DCOF	>0,60

**CHEMICAL CHARACTERISTICS**

<b>CHARACTERISTICS</b>	<b>STANDARD</b>	<b>VALUE</b>
Resistance to staining	UNE-EN-ISO 10545-14	Complies with the standars
Resistrance to chemicals and pool treatment products	UNE-EN-ISO 10545-13	Complies with the standars
Resistance to High concentration acids and bases	UNE-EN-ISO 10545-13	MIN HB
Resistance to Low concentration acids and bases	UNE-EN-ISO 10545-13	MIN LB